

## DESCRIPTION

Alkatane GE4760 is a medium molecular weight, easy flow High Density Polyethylene blow moulding grade with excellent organoleptic properties.

## **APPLICATION**

Alkatane GE4760 is particularly suited to the production of water, dairy and juice bottles.

## FOOD CONTACT / PRODUCT SAFETY

For food contact information please refer to the Regulatory Data Sheet at <u>genos.com</u>. For product safety information please refer to the Safety Data Sheet at <u>genos.com</u>.

Polymer Properties	Value <sup>1</sup>	Units	Test Method
Melt Index @ 190°C, 2.16 kg	0.6	g/10 min	ASTM D1238
Melt Index @ 190°C, 5.0 kg	2.4	g/10 min	ASTM D1238
Melt Index @ 190°C, 21.6 kg	48	g/10 min	ASTM D1238
Density	0.964	g/cm <sup>3</sup>	ASTM D1505

Moulding Properties	Value <sup>1</sup>	Units	Test Method
Tensile Strength at Yield <sup>2</sup>	30	MPa	ASTM D638
Flexural Modulus (1% Secant) <sup>3</sup>	1500	МРа	ASTM D790B
Izod Impact Strength @ -30°C	80	J/m	ASTM D256 Method A
ESCR - 10% Igepal (F <sub>50</sub> )	60	hrs	ASTM D1693 Condition B

1. Typical values - not to be construed as specifications.

2. At 50 mm/min cross head speed, type 4 dumbbell and 1.9 mm thickness.

3. At 12.7 mm/min cross head speed.

For up to date information, refer to genos.com

This information is offered solely for your consideration, investigation, verification and shall not be construed as a warranty or representation for which Qenos Pty Ltd assumes legal liability, except to the extent that such liability is imposed by legislation and cannot be excluded. Values quoted are the result of tests on representative samples, and the product supplied may not conform in all respects. Qenos Pty Ltd reserves the right to make any improvements or amendments to the composition of any grade or product without alteration to the code number. In using Qenos Pty Ltd's products, you must establish for yourself the most suitable formulation, production method and control tests, to ensure the uniformity and quality of your product in compliance with all laws. Qenos Pty Ltd ACN 054 196 771 is the registered user of the Qenos Logo which is registered trademark of Qenos Pty Ltd. "Alkatane" is a trademark of Qenos Pty Ltd.



Ingenious Transformations